

MOSHE 3000 FLEX

Water-repellent waterproofing agent for slabs, floors, and walls with infiltration and humidity problems

► Description

MOSHE 3000 FLEX was developed with nanotechnology, 100% inert minerals, and water-based acrylic resins. It has tested and proven hydrophobic properties as the best technical solution in the national and international market in the recovery and prevention of pathologies related to waterproofing walls, floors, and slabs. It is a flexible product, which creates a protective surface, providing high waterproofing and closing fissures and cracks even with small movements and expansions.

► Recommended for

- Internal and external floors and walls and/or in contact with soil moisture
- Basements, underground works, and retaining walls
- Rigid pavements, special art pieces, and bridges, sidewalks, precast concrete in general
- Swimming pools, reservoirs, cisterns, water tanks, tunnels and galleries, diaphragm walls
- Concrete slabs and fiber cement tiles
- Wood such as fences, posts, timber, and boards

► Advantages

It is a monocomponent liquid waterproofing and water-repellent product, providing great ease and speed in execution. It has great durability since it is composed of inert minerals. As it is liquid and monocomponent nanotechnology, it is ready to use and is easy to apply, just open the bucket and mechanically mix for 2 minutes before application. In this way, MOSHE 3000 FLEX prevents infiltrations, increases the durability of the construction, and prevents the proliferation of fungi and bacteria.

MOSHE 3000 FLEX creates a protective film, sealing all pores, fissures, and cracks in walls, floors, and slabs. It has excellent results for both positive and negative pressure of the water acting on the surface, ensuring excellent waterproofing, in addition to being resistant to ultraviolet rays.

5-year warranty according to performance reports proven by third-party laboratories, except for project failures, structural failures, or misuse of the material.

► **Technical Data**

Characteristics	
Density	1,15 g/cm ³
Soluble in water	Yes
pH	8 – 10
Recommended substrate application temperature	0 to 50°C
Recommended application ambient temperature	0 to 48°C
Material properties	
Product type	Mineral base powder and water-based resins
Aspect	Liquid
Color	Slightly bluish, and gray when dry
Storage	Store properly in original and intact packaging at temperatures between 5 and + 30°C
Shelf life	Packaged product shelf life, 1 years from the manufacture date
Packaging	3,6 L Bucket / 18 L Bucket
Moisture	0 %
Flammability	Non-flammable product (high flash point)
Odor	Characteristic
VOC	19,3 g/l (USEPA) Method 24

► **Application Method**

MOSHE 3000 FLEX must be applied without adding other components, as it is a one-component, ready-to-use product. Can be applied with a low wool roller, foam roller, or brush.

Application:

- 1) Check the weather forecast. Avoid applying in rainy weather or at risk of getting wet, except when this application is in a protected area. The best way to apply is with a wool paint roller. Do not apply the product to a damp surface, it must be 100% dry.
- 2) The substrate must be clean, without loose or disintegrating parts, and without the presence of oils, cement creams, mold release agents, or any other type of material that could cause the product to detach from the surface.
- 3) The application of the first coat should be done evenly, ensuring coverage of the entire surface to be waterproofed and leaving no gaps in the application for better visualization and use. The product is slightly bluish when fresh, and when dry, the final color is gray.
- 4) Apply the next coat only after the previous one has completely dried, around 1 to 3 hours, depending on weather conditions and local ventilation.
- 5) Recommended to apply 2 or 3 coats and use polyester mesh to reinforce places with corners, joints, fissures, drains, or holes.
- 6) After the product has dried, perform a thorough visual inspection to verify that the entire substrate has been covered. If there are points without application or with an inadequate application, perform an additional coat.

- 7) For surfaces with traffic of people or vehicles, it is necessary to apply mechanical protection or a finished floor above the application of Moshe 3000 Flex.
- 8) Close the packaging well at the end of the application if there is any leftover material. Otherwise, the product may dry out in contact with air, which will prevent future applications.
- 9) It is recommended to use only acrylic paints directly on the Moshe 3000 FLEX. Do not use water-based paints directly on Moshe 3000 Flex. Roughcast (3x1) can be applied between MOSHE 3000 FLEX and any other coating.
- 10) Structures to be treated with MOSHE 3000 FLEX must not have cracks or concrete failures greater than 2mm wide.
- 11) Pay attention to the expansion joints of the structural project; MOSHE 3000 FLEX does not replace specific elastomeric gaskets for expansion joints.
- 12) Do not apply on a substrate saturated with water. Residual water inside the substrate may evaporate, causing the formation of bubbles in the application or release (when this occurs, remove this bubble, and repeat the application in the removed area, according to the instructions above).
- 13) For planters, it is recommended to apply anti-root paint above the application of Moshe 3000 Flex.
- 14) When there are pipes, apply specific products for this purpose.
- 15) Carry out a water-tightness test for at least 72 hours, 48 hours after applying the product.
- 16) We are not responsible for design flaws or structural flaws, and it is highly recommended that you contact the Moshe 3000 technical department to clarify any doubts before applying Moshe 3000 Flex.
- 17) The product performance guarantee is linked to the forwarding to MOSHE 3000, by the product purchaser, via e-mail comercial@moshe3000.com, of a tightness report (with photographic report) of the substrate on which the product was applied, with the construction characterization data where it was used (address and particularization of the applied area), to be issued by the Construction Company or by the product application company, to be executed after the product application and before the mechanical protection, when applicable. Failure to send the tightness report exonerates MOSHE 3000 from any responsibility for the product performance. MOSHE 3000 is not responsible for damages caused to the product during the mechanical protection execution process or others after the tightness test. The purchaser acknowledges having access to the product performance reports and that the approval in the tightness test is sufficient to prove its adequate performance.

► Dosage

The average product yield is 3,78 m²/L per coat, depending on the roughness of the applied surface. The rougher, the lower the yield.

Reservoirs, swimming pools, retaining walls, uncovered slabs, and floor in contact with the ground: 3 coats

Other locations: 2 coats

► Personal protective equipment

Wear personal protective mask, natural rubber gloves, goggles or face protection, suitable clothing, and protective boots. If any symptoms of allergy, skin irritation, or eye contact, seek medical attention immediately.

Do not reuse packaging for food purposes. Care should be taken with opened packages in the presence of children, whether or not there's still product inside them.

▶ **Transport Limitations**

Maximum stacking of 3 buckets of 18 L or 5 buckets of 3.6 L.

▶ **Storage**

Store under cover, protecting the buckets from rain and sun, keep the containers tightly closed and protected from damage.

► Certification and Technical Reports

Product certified by the HBC (Healthy Building Certificate) qualified and certified product, as a product that does not cause any risk to human health and the environment, therefore, a healthy and sustainable product. The HBC grants the MOSHE 3000 product the title of Qualified and Certified Product registered under the Code PROD20201007BRAPR0012 with validity until 02/June/2023.

According to the SGS REPORT: Report of Product Testing Report – Interim Product: MOSHE 3000 FLEX Lab No.: 22-551, it was verified that in the test ASTM C1583 – Bond Strength to Concrete, the product resisted a pressure of 100 Psi in the tests with 7 and 28 days of cure, in the test ASTM D6904 – Wind-Driven Rain, it verified that the product resisted the spray of water for approximately 24 hours where water was sprayed at a rate of 60 to 70 gallons per hour and at 5 inches of water pressure (equivalent to dynamic pressure at a wind speed of 98 mph) without passing water and in the ASTM test E96 – Water Vapor Transmission, it was verified that when tested at a temperature of $73.4 \pm 2^\circ\text{F}$ and relative humidity of $50 \pm 2\%$, Water Vapor Transmission occurred - 20 thousand WFT (perm) of 3.7 years 28 days.

According to IPT's report TEST REPORT No. 1 131 867-203, it was verified that in the tests according to the ABNT NBR 10.787 test of Water Penetration under Positive Pressure, it was verified that there was no penetration of water in the specimen, after application of pressure of (0.10 ± 0.01) MPa for 48 hours, followed by application of pressure of (0.25 ± 0.01) MPa for 24 hours. According to the ABNT NBR 10,787 and 11,905 tests on Penetration of water under negative pressure, the product proved to be watertight up to a pressure of at least 0.10 MPa for 48 hours. According to the ABNT NBR 12.171 Test of Tensile Adhesion Resistance (minimum), the product showed an average resistance of 3.8 MPa, much higher than the standard that requires at least 0.5 MPa. According to the ABNT NBR 7462 test for Elongation at break (minimum) the product reached 3% and Elongation at break after aging (minimum) the product reached 5%, higher than the expansion of the concrete which is 0.03%.

According to IPT's report TEST REPORT No. 1 140 327-203, it was verified that in the tests according to ASTM D2369-20 - Standard Test Method for Volatile Content of Coatings (Procedure IPT6806 - Rev. 8), ASTM 4017-22 - Standard Test Method for Water in Paints and Paint Materials by Karl Fischer Method and United States Environmental Protection Agency (USEPA) Method 24 - Determination of Volatile Matter Content, Water Content, Density, Volume Solids, And Weight Solids of Surface Coatings - method for water-based coatings, it was found that the Volatile Matter Content, non-aqueous - g/L of MOSHE 3000 FLEX is 19.3 g/L which is well below the limits required by the USGBC LEED Certification which according to South Coast Air Quality Management District (SCAQMD) Rule 1113, effective June 3, 2011 is 400 g/L.

► Observations

Responsible Chemist: Eder de Souza CRQ-IV SP 04414353

Technician Responsible Developer: Marcos Alberto Casado Pereira
Produced by Moshe Materiais de Construção Ltda Ltd EPP CNPJ 02.732.735/001
Rua Zélia, 454 Bairro Assunção São Bernardo do Campo / SP – Brazil
Moshe 3000 Brasil Customer Service [+55 11 97673 1458](tel:+5511976731458)

The information contained in this document is based on our knowledge for your help and guidance. We point out that the performance of the products depends on the conditions of surface preparation, application, and storage, which are not under the responsibility of Moshe 3000. The performance depends on the application technique, equipment, and substrate conditions. Therefore, we do not assume any responsibility regarding the yield and performance of any nature as a result of misuse of the product and misapplication. This product requires specialized labor for application. For more information, consult the technical department.